



Miragrid® 2XT Biaxial Geogrid for Retaining Wall Reinforcement

TenCate® develops and produces materials that function to increase performance, reduce costs and deliver measurable results by working with our customers to provide advanced solutions.

Miragrid® 2XT geogrid is a high strength, high tenacity, high molecular weight polyester geogrid manufactured for use in low height segmental retaining walls and reinforced slope facing stability.

Miragrid® 2XT geogrid is woven and then coated with a polymer coating to provide dimensional stability. The high molecular weight, high tenacity polyester yarns used in the Miragrid® 2XT geogrid result in excellent creep resistance. The high molecular weight polyester fibers are also resistant to the potentially degradative effects of hydrolysis and chemical attack in the range of pH normally encountered in reinforced soil environments.

The Difference Miragrid® 2XT Geogrid Makes:

- Biaxial strength. Same strength in both directions.
- · Convenient packaging. Small roll packaging for easier handling and storage.
- Roll widths. Available in 4 feet wide (POP bags), 6 feet wide rolls on pallets and 12

feet wide rolls for maximum flexibility.

- · Flexible and tough. Delivers immediate soil to geogrid stress transfer ensuring minimal movement of soil structure.
- Lightweight. At least 33% lighter than most rigid geogrids but durable for construction.
- · Cost effective. Creep resistant polyester fibers provide a higher allowable tensile strength, minimizing the required number of geogrid layers.
- · Easy handling. No sharp edges which may injure workers.

PACKAGING

Miragrid® 2XT is available in point-of-purchase (POP) display packaging or in commercial size rolls.

The POP display box contains 10 rolls, each 4 feet wide x 45 feet long (180 ft²), placed in a clear bag. Each POP display box is printed with quantity estimating information (as shown at right).

INSTALLATION GUIDELINES*

The POP packed rolls can either be purchased in the full box (10 rolls/box) or in 3 roll bundles without a box.

Place Miragrid® 2XT a maximum vertical spacing of every 2 SRW units. Provide adequate drainage and compacted fill per SRW unit manufacturer's instructions. Chart is for estimating purpose only. Final design should be performed by a registered, professional engineer to meet all local codes and regulations. No provisions have been made for global/external stability, nor site topography. Use higher strength Miragrid® geogrids in walls over 6 feet in height.

* These guidelines serve as a general basis for installation. Detailed instructions are available from your TenCate® representative.












Miragrid® 2XT Biaxial Geogrid

for Retaining Wall Reinforcement

Property	Test Method	2XT
Polymer (coating)	_	PET (PVC)
Ultimate Wide Width Tensile Strength*	ASTM D6637	2000 lbs/ft (29.2 kN/m)
Creep Reduced Strength*	ASTM D5262	1266 lbs/ft (18.5 kN/m)
Long Term Design Strength* (In Type 3 Backfill: sand, silt,	GRI-GG4 clay)	1096 lbs/ft (16.0 kN/m)
*Machine Direction and Cros	ss Machine Direction	

Roll Packaging	Units	POP Bag	Commercial Pack
Roll Width	ft (m)	4 (1.22)	6.0 (1.8)
Roll Length	ft (m)	45 (13.7)	150 (45.7)
Est. Roll Wt.	lbs (kg)	10 (4.5)	47 (21)
Area	yd² (m²)	20 (16.7)	100 (82.3)
Rolls/pallet	-	36	30
BOX Packaging	Units	POP Bags	Commercial Pack
Rolls/box		10	-
Boxes/pallet		4	-
Box height	in (cm)	48.5 (123)	_
Dox noight	III (GIII)	40.5 (125)	
Box width	in (cm)	22.5 (57)	-

Miragrid® 2XT Geogrid



	Miragrid® 2XT	# 2XT of layers	
Wall Height, H ft (m)	Roll Width, W ft (m)	6″ tall blocks	8" tall blocks
3 (0.91)	4.0 (1.22)	3	2
4 (1.22)	4.0 (1.22)	4	2
5 (1.52)	4.0 (1.22)	5	3
6 (1.83)	4.0 (1.22)	6	4

Miragrid® 2XT Quantity Determination

Layers x W x length of wall = # of rolls 180 square foot

Example: A SRW wall using 6" tall blocks is 6ft tall x 30ft long. Derived from table: H = 6ft, W = 4ft, & 6 layers. $\frac{6 \text{ layers } x \text{ } 4ft \text{ } x \text{ } 30ft}{180\text{sq. } ft \text{ per roll}}$

TenCate® Geosynthetics Americas assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate® Geosynthetics Americas disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corpration.

© 2012 TenCate Geosynthetics North America

PDS.2XT0312

365 South Holland Drive Tel 800 685 9990 Fax 706 693 4400 Pendergrass, GA 30567 Tel 706 693 2226 www.mirafi.com







